

### ABSTRACT OF DISCLOSURE

A photo- resist mask of organic compound is stripped off after the pattern transfer to a layer thereunder, wherein the photo- resist mask is firstly exposed to vapor of organic solvent for reducing the thickness through a reflow, and, thereafter, the photo- resist mask is ashed in an oxygen plasma, whereby the dry ashing is completed within a short time period by virtue of the reduction of thickness.